

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

27

(11) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(13) 特許公報公開番号

特開平 8-125066

(14) 公開日 平成 8 年 (1996) 5 月 17 日

(51) Int. Cl.

H01L 23/12

23/12

図別記号

特許庁登録番号

F 1

特許庁表示箇所

A 5921-4E

H01L 23/12

審査請求 未請求 特許料の払込 F D (金 7 頁)

(11) 出願番号

特願 6-284536

(12) 出願日

平成 6 年 (1994) 10 月 26 日

(13) 出願人

000002897

大日本印刷株式会社

東京都新宿区市谷江坂町一丁目 1 番 1 号

(14) 発明者

八木 裕

東京都新宿区市谷江坂町一丁目 1 番 1 号

大日本印刷株式会社内

(15) 発明者

森田 達彦

東京都新宿区市谷江坂町一丁目 1 番 1 号

大日本印刷株式会社内

(16) 代理人



弁護士 小西 修典

(54) [発明の名称] 絶縁防止型半導体装置とそれを用いられるリードフレーム、及び絶縁防止型半導体装置の製造方法

(57) [要約]

【目的】 更なる絶縁防止型半導体装置の高集積化、高信頼化が求められている中、半導体装置パッケージサイズにおけるチップの占有率を上げ、半導体装置の小型化に対応させ、同時に従来の T S O P 等の小型パッケージに類似であった更なる多ピン化を実現した絶縁防止型半導体装置を提供する。

【構成】 半導体装置の端子側の面に、半導体装置の端子と電気的に接続するための内部端子部と、半導体装置の端子側の面へ露出して外部へと向く外部端子部への接続のための外部端子部と、前記内部端子部と外部端子部とを導通する接続リード部とを一体とした複数のリード部とを、絶縁性材料層を介して、露出して設けてあり、且つ、絶縁性材料層への露出のための半導体からなる外部電極を前記複数のリード部の外部端子部に導通させ、少なくとも前記半導体からなる外部電極の一部は露出部より外部に露出させて設けている。



【請求項 1】

半導体素子の端子部の面に、半導体素子の端子と電気的に接続するための内部端子部と、半導体素子の端子部の面へ固定して外部へと向く外部端子部への接続のための外部端子部と、前記内部端子部と外部端子部とを接続する接続リード部とを一体としたリード部を形成し、絶縁性材料層を介して、固定して設けてあり、且つ、図形基板等への実装のための半田からなる外部電極を前記接続部のリードの外部端子部に接続させ、少なくとも前記半田からなる外部電極の一部は前記より外部に突出させて設けていることを特徴とする半導体装置。

【請求項 2】 請求項 1 において、半導体素子の端子は半導体素子の端子部の一方の辺の端中心部上に設けてあり、リード部は接続部の端子を挟むように対向し前記一方の辺に設けられていることを特徴とする半導体装置。

【請求項 3】 半導体素子の端子と電気的に接続するための内部端子部と、外部端子部と接続するための外部端子部と、前記内部端子部と外部端子部とを接続する接続リード部とを一体とし、該外部端子部を、接続リード部を介して、リードフレーム面から固定する一方向側へ突出させ、対向し先端部同士で接続部を介して接続する一方の内部端子部を接続部から設けてあり、且つ、各外部端子部の先端で、接続リード部と接続し、一体として全体を保持する外部部を設けていることを特徴とするリードフレーム。

【請求項 4】 半導体素子の端子部の面に、半導体素子の端子と電気的に接続するための内部端子部と、半導体素子の端子部の面へ固定して外部へと向く外部端子部への接続のための外部端子部と、前記内部端子部と外部端子部とを接続する接続リード部とを一体とした接続部のリード部とを、絶縁性材料層を介して、固定して設けてあり、且つ、図形基板等への実装のための半田からなる外部電極を前記接続部のリードの外部端子部に接続させ、少なくとも前記半田からなる外部電極の一部は前記より外部に突出させて設けている半導体装置の製造方法であって、少なくとも、(A) エッチング加工で、半導体素子の端子と電気的に接続するための内部端子部と、外部端子部と接続するための外部端子部と、内部端子部と外部端子部とを接続する接続リード部とを一体とし、該外部端子部を、接続リード部を介して、リードフレーム面から固定する一方向側へ突出させ、対向し先端部同士で接続部を介して接続する一方の内部端子部を接続部から設けてあり、且つ、各外部端子部の先端で、接続リード部と接続し、一体として全体を保持する外部部を設けているリードフレームを形成する工程、(B) リードフレームの外部端子部でない面（裏面）に材料を設け、打ち込み金型により、内面する内部端子部を形成する製造部と該製造部に対応する位置に設け

られた材料とを打ち込み、リードフレームの打ち込まれた部分が半導体素子の端子部にくるようにして、前記材料を介して、リードフレーム全面を半導体素子へ固定する工程、(C) リードフレームの外面を金具不溶の部分に打ち込みを金型により切断する工程、

(D) 半導体素子の端子部と、切断部で、半導体素子へ固定された内部端子部の先端部とをワイヤボンディングした後に、前記により外部端子部のみを外部に突出させて全体を固定する工程、(E) 前記外部に突出した外部端子部面に半田からなる外部電極を形成する工程、を含むことを特徴とする半導体装置の製造方法。

【発明の詳細な説明】

(0001)

【産業上の利用分野】 本発明は、半導体素子を固定する半導体装置の半導体装置（プラスチックパッケージ）に関し、特に、実装密度を向上させ、且つ、多ピン化に対応できる半導体装置とその製造方法に関する。

(0002)

【従来の技術】 近年、半導体装置は、高集積化、小型化技術の進歩と電子機器の高性能化と省資源化の傾向（時代）から、LSI の ASIC に代替されるように、ますます高集積化、高機能化になってきている。これに伴い、リードフレームを用いた半導体装置プラスチックパッケージにおいても、その開発のトレンドが、SOJ (Small Outline J-Lead Package) や QFP (Quad Flat Package) のような高実装密度のパッケージを経て、TSOP (Thin Small Outline Package) の開発による薄型化を主眼としたパッケージの小型化へ、さらにはパッケージ内部の3次元化によるチップ収容効率向上を目的としたLOC (Lead On Chip) の開発へと進展して来た。しかし、半導体装置半導体装置パッケージには、高集積化、高機能化とともに、更に一層の多ピン化、薄型化、小型化が求められており、上記従来のパッケージにおいてもチップ表面部分のリードの引き出しがあるため、パッケージの小型化に障壁が見えて来た。また、TSOP等の小型パッケージにおいては、リードの引き出し、ピンピッチから多ピン化に対しても障壁が見えて来た。

(0003)

【発明が解決しようとする課題】 上記のように、更なる半導体装置半導体装置の高集積化、高機能化が求められており、半導体装置半導体装置パッケージの一層の多ピン化、薄型化、小型化が求められている。本発明は、このような状況のもと、半導体装置パッケージサイズにおけるチップの占有率を上げ、半導体装置の小型化に対応させ、図形基板への実装密度を低減せよ、即ち、図形基板への実装密度を向上させることが出来る半導体装置半導体装置を開発しようとするものである。また、前記

に従来の T S O P 系の小型パッケージに匹敵する多ピン化を實現しようとするものである。

(0 0 0 4)

(注) を解決するための手段) 本発明の絶縁防止型半導体装置は、半導体素子の端子側の面に、半導体素子の端子と電気的に絶縁するための内部電子部と、半導体素子の端子側の面へ直交して外部へと向く外部電極への接続のための外部電子部と、前記内部電子部と外部電子部とを連結する接続リード部とを一体とした複数のリード部とを、絶縁性基材層を介して、配置して設けており、且つ、絶縁性基材層への実装のための半田からなる外部電極を前記複数の各リードの外部電子部に接続させ、少なくとも前記半田からなる外部電極の一部は前記基材層より外部に突出させて設けていることを特徴とするものである。尚、上記において、内部電子部と外部電子部とを一体とした複数のリード部の配列を半導体素子の端子側面に二次元的に配列し、外部電極部を半田ボールにて形成することにより B C A (B a l l G r i d A r r a y) タイプの絶縁防止型半導体装置とすることとする。

(0 0 0 5) そして、上記において、半導体素子の端子は半導体素子の端子側の一面の辺の中心位置上にそって配置されており、リード部は複数の端子を挟むように対向し前記一面の辺に沿って設けられていることを特徴とするものである。また、本発明のリードフレームは、絶縁防止型半導体装置用のリードフレームであって、半導体素子の端子と電気的に絶縁するための内部電子部と、外部電極とを接続するための外部電子部と、前記内部電子部と外部電子部とを連結する接続リード部とを一体とし、該外部電子部を、接続リード部を介して、リードフレーム面から突出する一方の側面に突出させ、対向し先端部同士で接続部を介して接続する一方の内部電子部を接続設けており、且つ、各外部電子部の外側で、接続リード部と連絡し、一体として全体を保持する外側部を設けていることを特徴とするものである。尚、上記リードフレームにおいて、内部電子部と外部電子部とそれらを連結する接続リード部とを一体とした複数を複数のリードフレーム面に二次元的に配列するして形成することにより B C A (B a l l G r i d A r r a y) タイプの絶縁防止型半導体装置用のリードフレームとすることとする。

(0 0 0 6) 本発明の絶縁防止型半導体装置の製造方法は、半導体素子の端子側の面に、半導体素子の端子と電気的に絶縁するための内部電子部と、半導体素子の端子側の面へ直交して外部へと向く外部電極への接続のための外部電子部と、前記内部電子部と外部電子部とを連結する接続リード部とを一体とした複数のリード部とを、絶縁性基材層を介して、配置して設けており、且つ、絶縁性基材層への実装のための半田からなる外部電極を前記複数の各リードの外側電子部に接続させ、少なくとも前記半田からなる外部電極の一部は前記基材層より外部に突出させて設けていることを特徴とするものである。尚、上記において、内部電子部と外部電子部とを一体とした複数のリード部の配列を半導体素子の端子側面に二次元的に配列し、外部電極部を半田ボールにて形成することにより B C A (B a l l G r i d A r r a y) タイプの絶縁防止型半導体装置とすることとする。

図 1 から図 4 は本発明の一例に示す絶縁防止型半導体装置の製造方法を示すものであり、(A) エッチング加工にて、半導体素子の端子と電気的に絶縁するための内部電子部と、外部電極とを形成するための外部電子部と、前記内部電子部と外部電子部とを連結する接続リード部とを一体とし、該外部電子部を、接続リード部を介して、リードフレーム面から突出する一方の側面に突出させ、対向し先端部同士で接続部を介して接続する一方の内部電子部を接続設けており、且つ、各外部電子部の外側で、接続リード部と連絡し、一体として全体を保持する外側部を設けているリードフレームを形成する工程、(B) 前記リードフレームの外側電子部側でない面 (裏面) に絶縁層を設け、前記絶縁層により、対向する内部電子部同士を接続する接続部と該絶縁層に形成する位置に設けられた絶縁層の開口部とを、リードフレームの開口部とを形成した部分が半導体素子の端子部にくるようにして、前記絶縁層を介して、リードフレーム全体を半導体素子へ実装する工程、(C) リードフレームの外側部を含む不要部分を開口部を金型により切断する工程、(D) 半導体素子の端子部と、切断されて、半導体素子へ実装された内部電子部の先端部とをワイヤボンディングした後に、前記により外部電子部側のみを外部に突出させて全体を封止する工程、(E) 前記封止に突出した外部電子部面に半田からなる外部電極を形成する工程、とを含むことを特徴とするものである。

(0 0 0 7)

(作用) 本発明の絶縁防止型半導体装置は、上記のような構成にすることにより、半導体装置パッケージサイズにおけるチップの占有率を上げ、半導体装置の小型化に対応できるものとしている。即ち、半導体装置の内部電極への実装性を確保し、絶縁性基材層への実装性の向上を可能としている。詳しくは、内部電子部、外部電子部とを一体とした複数のリード部を半導体素子面に絶縁層を介して固定し、前記外部電子部に半田からなる外部電極部を接続させていることより、装置の小型化を達成している。そして、上記半田からなる外部電極部を、半導体素子面に非平行な面を二次元的に配列することにより、半導体装置の多ピン化を可能としている。半田からなる外部電極部を半田ボールとし、二次元的には外部電極部を配列した場合には B C A タイプとなり、半導体装置の多ピン化にも対応できる。また、上記において、半導体素子の端子が半導体素子の端子側の一面の辺の中心位置上にそって配置され、リード部は複数の端子を挟むように対向し前記一面の辺に沿って設けられており、従来の装置とし、高密度に接続した構造としている。本発明のリードフレームは、上記のような構成にすることにより、上記絶縁防止型半導体装置の製造を可能とするものであるが、通常のリードフレームと同様のエッチング加工による。

とがでる。本発明の樹脂封止型半導体装置の製造方法は、上記リードフレームを用いて、リードフレームの外装部封止でない面（底面）に地層材を形成し、これを合金により、方向する内部電子部材を形成する導線部と導線部に対応する位置に形成された地層材とを形成し、リードフレームの形成された部分が半導体素子の端子部にくるようにして、前記導線材を介して、リードフレーム全体を半導体素子へ搭載し、リードフレームの外装部を含む半導体装置の部分を合金により切断することにより、内部電子と外部電子を一体化した装置を多数半導体装置上に形成した。本発明の半導体装置の小型化が可能で、且つ、多ピン化が可能で樹脂封止型半導体装置の作製を可能としている。

【0008】

【実施例】本発明の樹脂封止型半導体装置の実施例を以下、図にそって説明する。図1(a)は本実施例樹脂封止型半導体装置の断面図であり、図1(b)は上面図である。図1中、100は樹脂封止型半導体装置、101は半導体素子、102はリード部、102Aは内部電子部、102Bは外部電子部、102Cはリード部、101Aは端子部（パッド部）、103はワイヤ、104は地層材、105は導線部、106は半田（ペースト）からなる外部電極である。本実施例樹脂封止型半導体装置は、前述するリードフレームを用いたもので、内部電子部102A、外部電子部102Bを一体化した半導体のリード部102を多数半導体素子101上に地層材104を介して形成し、且つ、外部電子部102B先に半田からなる外部電極を導線部105より外部へ突出させて設けた。パッケージ構造が半導体装置の面側に形成する樹脂封止型半導体装置であり、図1(a)へ形成される際には、半田（ペースト）を形成、硬化して、外部電子部102Bが外部電極と電気的に接続される。本実施例樹脂封止型半導体装置は、図1(b)に示すように、半導体素子101の端子部（パッド部）101Aは半導体素子の中心部とは若干方向して2箇所、中心部1に附して形成されており、リード部102は、内部電子部102Aが前記端子部（パッド部）に附した位置に半導体素子101の部の外側に中心部を挟み対向するように形成されている。外部電子部102Bは内部電子部102Aから形成リード部102Cを介して附して形成し、ほぼ半導体素子の前面まで達した位置で半導体素子面に固定する方向に、形成リード102Cが水平に曲がり、外部電子部102Bはその先端に位置し、半導体素子の面に平行な方向で一元的に配列をしている。即ち、中心部1を挟み2列の外部電子部102Bの配列を設けている。そして、各外部電子部102Bを導線部105より外部に突出させて設けている。1、地層材104としては、100μm程度のポリイ

と酸を用いたが、他には、シリコン系ポリイミド（TA）715（住友ヘラクライト株式会社）や有機化合物系HCS200（三井物産株式会社）等が用いられる。上記実施例では、半田ペーストからなる外部電極であるが、この部分は半田ボールに代えてもよい。尚、本実施例樹脂封止型半導体装置は、上記のように、パッケージ構造が半導体装置の面側に形成する、面側に小型化されたパッケージであるが、取り付け方向について、41、0mm以下にすることができ、厚さ10mmに達してよいものである。本実施例においては外部電極部を、半導体素子の端子部（パッド部）に附した2列に配列したが、半導体素子の端子部の位置を二次元的に配列し、内部電子部と外部電子部との一体化した装置を形成し、半導体素子の端子部に二次元的に配列して形成することにより、半導体素子の、一面の多ピン化に十分対応できる。

【0009】次に、本発明のリードフレームの実施例をあげ、図に示して説明する。本実施例リードフレームは、上記実施例半導体装置に用いられたものである。図2は本実施例リードフレームの断面図を示すもので、図2中、200はリードフレーム、201は内部電子部、202は外部電子部、203は形成リード部、204は導線部、205は外部電極である。リードフレームは42合金（Ni42%のFe合金）からなり、リードフレームの厚さは、内部電子部のある厚さ部で0.05mm、外部電子部のある厚さ部で0.2mmである。内部電子部の方向する先端部同士を接続する導線部205は厚さ（0.05mm厚）に形成されており、前述する半導体装置を形成する際の形成合金にて形成し、良い接続となっている。本実施例では外部電子部202は丸状であるが、これに限定はされない。また、リードフレーム材料として42合金を用いたがこれに限定されない。銅合金でもよい。

【0010】次に、上記実施例リードフレームの製造方法を図を用いて簡単に説明する。図4は本実施例リードフレームを製造した工程を示したものである。先ず、42合金（Ni42%のFe合金）からなる、厚さ0.2mmのリードフレーム原料300を準備し、板の両面を酸洗を行いAく洗浄処理した（図3(a)）は、リードフレーム原料300の両面に感光性のレジスト301を塗布し、乾燥した。（図3(b)）。

次に、リードフレーム原料300の両面から所定のパターン図を用いてレジストの所定の部分のみを露光を行った後、現像処理し、レジストパターン301Aを形成した。（図3(c)）

尚レジストとしては東京化成工業株式会社のネガ型レジスト（PMERレジスト）を使用した。次に、レジストパターン301Aを耐熱処理として、57°C、48時間の硬化後二次乾燥を経て、リードフレーム原料300の両面からスプレエッチングして、外部電極

の平面図を図 2 に示したリードフレームを作製した (図 3 (c))。図 2 (b) のは、図 2 の A1-A2 における断面図である。これは、レジストを剥離した後、焼付処理を施した後、所定の箇所 (内部端子部分を含む領域) のみに金メッキ処理を行った。(図 3 (e)) 尚、上記リードフレームの製造工程においては、図 2 (b) に示すように、厚肉部と薄肉部を形成するための、外装端子形成箇所からのエッチング (露出) を多く行い、反対側側からは少なめにエッチング (露出) を行った。また、金メッキに加え、銅メッキやパラジウムメッキでも良い。上記のリードフレームの製造方法は、1 枚の半導体装置を作製するために必要なリードフレーム 1 枚の製造方法であるが、通常は半導体装置から、リードフレーム部材をエッチング加工する後、図 2 に示すリードフレームを複数個部付けした状態で作製し、上記の工程を行う。この場合は、図 2 に示す外装部 205 の一部に露出する部材 (図示していない) をリードフレームの外側に付けて部付け状態とする。

(0011) 次に、上記のようにして作製されたリードフレームを用いた、本発明の露出防止型半導体装置の製造方法の実施例を図に示して説明する。図 4 は、本実施例の露出防止型半導体装置の製造工程を示すものである。図 5 に示すようにして作製されたリードフレーム 400 の外装端子部 402 形成部 (後面) と対向する裏面に、ポリイミド系熱硬化型の絶縁性材料 (テープ) 401 (日立化成株式会社製、HM122C) を、400°C、6Kg/m² で 1.0 秒間圧着して貼りつけた (図 4 (a))。この状態の平面図を図 5 に示す。この状態で、

ちばさ金型 405A、405B にて (図 4 (b))、対向する内部端子部の先端部を露出する露出部 403 と、その部分の絶縁性材料 (テープ) 401 とを打ち抜いた。(図 4 (c))

次いで、外装部 404 をおよび圧着用金型 406A、406B を用い、外装部 404 を含む不要部分を切り離す (図 4 (d)) と同時に、絶縁性材料 404 を介して半導体素子 407 上にリード部 408 の熱圧着を行った。(図 4 (e))

尚、この図 4 (d) に示す、露出リードと露出してリードフレーム全体を穿入している外装部 204 を含む不要部分を切り離しは、露出防止した後に付しても良い。この場合には、通常の厚層リードフレームを用いた OFP パッケージ等のようにダムバー (図示していない) を設けると良い。リード部 410 を半導体素子 411 へ接続した後、ワイヤ 414 により、半導体素子の端子 (パッド) 411A とリード部 410 の内部端子 410A とを電気的に接続した。(図 4 (f))

その後、所定の金型を用い、エポキシ系の樹脂 415 でリード部 410 の外装端子部 410B のみを固定させ、全体を封止した。(図 4 (g))

ここでは、厚肉の金型 (図示していない) を用いたが、

厚肉の面 (外装端子部) を丹し露出防止された。また、しき金型は必要としない。次いで、露出されている外装端子部 410B 上に半導体素子をスクリーン印刷により塗布し、半導体素子 (ペースト) からなる外装端子部 416 を作製し、本発明の露出防止型半導体装置を作製した。(図 4 (h))

尚、半導体素子からなる外装端子部 416 の作製は、スクリーン印刷に限定されるものではなく、リフローまたはポッティング等でも、図 4 厚肉と半導体素子の形成に必要な厚肉の半導体素子が得られれば良い。

(0012)

【発明の効果】本発明は、上記のように、更なる露出防止型半導体装置の高度化、高信頼化が求められる状況のもと、半導体装置パッケージサイズにおけるチップの占有部を上げ、半導体装置の小型化に対応させ、図 4 厚肉への実装部材を低減できる、即ち、図 4 厚肉への実装部材を向上させることが出来る半導体装置の提供を可能としたものであり、同時に従来の T SOP 等の小型パッケージに適用であった更なる多ピン化を実現した露出防止型半導体装置の提供を可能としたものである。

【図面の簡単な説明】

【図 1】本発明の露出防止型半導体装置の概略断面図及び裏面図

【図 2】本発明のリードフレームの平面図

【図 3】本発明のリードフレームの製造工程図

【図 4】本発明の露出防止型半導体装置の製造工程図


【図 5】本発明のリードフレームに絶縁性材料を貼り付けた状態の平面図

【符号の説明】

100	露出防止型半導体装置
101	半導体素子
101A	端子部 (パッド部)
102	リード部
102A	内部端子部
102B	外装端子部
102C	露出リード部
103	ワイヤ
104	絶縁性材料
105	樹脂部
106	半導体 (ペースト) からなる外装
200	リードフレーム
201	内部端子部
202	外装端子部
203	露出リード部
204	端子部
205	外装部
300	リードフレーム部材
301	レジスト

303A 内装端子部
 303B 外装端子部
 304 送信部
 305 金メッキ部
 306 外装部
 400 リードフレーム
 401 絶縁層基板(テープ)
 402 外装端子部
 403 送信部

(図1)




(1)


RM 8-125066

405A, 405B 1750252
 406A, 406B 1750252
 410 リード部
 410A 内装端子部
 410B 外装端子部
 410C 絶縁リード部
 411 半導体素子
 411A ワイヤ
 415 絶縁部


(図2)




(図 3)



(図 5)



(図 4)



Japan se Patent Laid-Open Publication No. Heisei 8-125066

[TITLE OF THE INVENTION]

Resin Encapsulated Semiconductor Device, Lead Frame
5 Used Therein, and Fabrication Method for the Resin
Encapsulated Semiconductor Device

[CLAIMS]

1. A resin encapsulated semiconductor device
10 comprising:
a semiconductor chip;
a plurality of leads fixedly attached to a terminal-
end surface of the semiconductor chip by an insulating
adhesive interposed between the semiconductor chip and the
15 leads, each of the leads including integral portions, that
is, an inner terminal portion adapted to be electrically
connected to an associated one of terminals of the
semiconductor chip, an outer terminal portion extending
outwardly in a direction orthogonal to the terminal-end
20 surface of the semiconductor chip and adapted to be
connected to an external circuit, and a connecting lead
portion adapted to connect the inner and outer terminal
portions to each other; and
outer electrodes each connected to the outer terminal
25 portion of an associated one of the leads and made of

solder to allow the semiconductor device to be mounted on a circuit board, at least a part of the outer leads being externally exposed from a resin encapsulation.

5 2. The resin encapsulated semiconductor device according to claim 1, wherein the terminals of the semiconductor chip are arranged along a substantially center line between a pair of sides of the semiconductor chip on the terminal-end surface of the semiconductor chip,
10 and the leads are arranged in two facing sets along the sides of the semiconductor chip, respectively, in such a fashion that the terminals of the semiconductor chip are interposed between the two facing lead sets.

15 3. A lead frame comprising:

 a plurality of leads each including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of a semiconductor chip, an outer terminal portion adapted to
20 be connected to an associated one of terminals of an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other;

 each of the outer terminal portions of the leads
25 being protruded in a direction orthogonal to a lead frame

surface via an associated one of the connecting lead portions;

the inner lead portions of the leads being arranged in pair in such a fashion that the leads of each lead pair have facing tips, respectively;

connecting portions each adapted to connect the facing tips of the leads included in an associated one of the lead pairs; and

an outer frame portion arranged outside the outer terminal portions and connected to the connecting lead portions in such a fashion that they form an integral structure together, thereby protecting the entire portion of the lead frame.

4. A method for fabricating a semiconductor device including a semiconductor chip, a plurality of leads fixedly attached to a terminal-end surface of the semiconductor chip by an insulating adhesive-interposed between the semiconductor chip and the leads, each of the leads including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of the semiconductor chip, an outer terminal portion extending outwardly in a direction orthogonal to the terminal-end surface of the semiconductor chip and adapted to be connected to an external circuit,

and a connecting lead portion adapted to connect the inner and outer terminal portions to each other; and outer electrodes each connected to the outer terminal portion of an associated one of the leads and made of solder to allow the semiconductor device to be mounted on a circuit board, at least a part of the outer leads being externally exposed from a resin encapsulate, comprising the steps of:

(A) fabricating a lead frame including a plurality of leads each including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of a semiconductor chip, an outer terminal portion adapted to be connected to an associated one of terminals of an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other, each of the outer terminal portions of the leads being protruded in a direction orthogonal to a lead frame surface via an associated one of the connecting lead portions, the inner lead portions of the leads being arranged in pair in such a fashion that the leads of each lead pair have facing tips, respectively, connecting portions each adapted to connect the facing tips of the leads included in an associated one of the lead pairs, and an outer frame portion arranged outside the outer terminal portions and connected to the connecting lead portions in such a fashion that they form

an integral structure together, thereby protecting the entire portion of the lead frame;

(B) applying an insulating layer to a surface of the lead frame opposite to the outer terminal portions, punching out the connecting portions adapted to connect facing ones of the inner lead portions to each other along with portions of the insulating layer respectively arranged at regions corresponding to the connecting portions by use of punching dies, aligning the punched portions of the lead frame with the terminals of the semiconductor chip, and mounting the entire portion of the lead frame on the semiconductor chip by the adhesive interposed therebetween;

(C) cutting off unnecessary portions of the lead frame including the outer frame portion by use of punching dies, thereby removing the cut-off portions;

(D) wire-bonding the terminals of the semiconductor chip with tips of the inner terminal portions mounted on the semiconductor chip, and encapsulating the semiconductor chip and the lead frame by a resin while allowing a surface of the lead frame toward the outer terminal portions to be externally exposed; and

(E) forming outer electrodes made of solder on the exposed lead frame surface toward the outer terminal portions.

[DETAILED DESCRIPTION OF THE INVENTION]

[FIELD OF THE INVENTION]

The present invention relates to a resin encapsulated semiconductor device (plastic package) in which a semiconductor chip is packaged, and more particularly to a semiconductor device configured to achieve an improvement in mounting density or to have a multi-pinned structure and a method for manufacturing such a semiconductor device.

10 [DESCRIPTION OF THE PRIOR ART]

Recently, semiconductor devices have been developed to have a higher integration degree and a higher performance by virtue of developments of techniques associated with an increase in integration degree and miniaturization and in pace with the tendency of electronic appliances to have a high performance and a light, thin, simple, and miniature structure. A representative example of such semiconductor devices is an ASIC of LSI. For instance, developments of resin encapsulated semiconductor device plastic packages have been advanced from surface-mounting packages such as SOJs (Small Outlined-Leaded Packages) or QFPs (Quad Flat Packages) to packages having a miniature structure mainly achieved in accordance with a thinness obtained by virtue of developments of TSOPs (Thin Small Outline Packages) or to LOC (Lead On Chip) structures

adapted to achieve an improvement in the chip packaging efficiency by virtue of developments of an internal three-dimensional package structure. In addition to an increase in integration degree and improvement in performance, there has also been growing demand for an increase in the number of pins, thickness, and miniaturization of resin encapsulated semiconductor packages. In the above mentioned conventional packages, however, there is a limitation in miniaturization because those packages have a structure in which leads are arranged around a chip. Similarly, leads are arranged around a chip in the case of miniature packages such as TSOPs. In such packages, there is also a limitation in increasing the number of pins due to the pin pitch used.

15

[SUBJECT MATTERS TO BE SOLVED BY THE INVENTION]

As mentioned above, there has been demand for an increase in integration degree and improvement in performance of resin encapsulated semiconductor devices. Also, there has also been growing demand for an increase in the number of pins, thickness, and miniaturization of resin encapsulated semiconductor packages. In such situations, the present invention makes it possible to increase the occupancy degree of a chip in a semiconductor package with a limited size while reducing the mounting area of the

25

semiconductor package on a circuit board to achieve a miniaturization of the resulting semiconductor device. That is, the present invention is adapted to provide a resin encapsulated semiconductor device capable of achieving an improvement in the mounting density thereof on a circuit board. Also, the present invention is adapted to achieve an increase in the number of pins which is difficult in miniature packages such as conventional TSOPs.

10 (MEANS FOR SOLVING THE SUBJECT MATTERS)

The resin encapsulated semiconductor device of the present invention is characterized in that it comprises: a semiconductor chip; a plurality of leads fixedly attached to a terminal-end surface of the semiconductor chip by an insulating adhesive interposed between the semiconductor chip and the leads, each of the leads including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of the semiconductor chip, an outer terminal portion extending outwardly in a direction orthogonal to the terminal-end surface of the semiconductor chip and adapted to be connected to an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other; and outer electrodes each connected to the outer terminal portion of an associated one of the

leads and made of solder to allow the semiconductor device to be mounted on a circuit board, at least a part of the outer leads being externally exposed from a resin encapsulate. The above semiconductor device can be embodied into a BGA (Ball Grid Array) type resin encapsulated semiconductor device by arranging a plurality of leads each having an inner terminal portion and an outer terminal portion integral with each other in a two-dimensional fashion on the terminal-end surface of the semiconductor chip and forming the outer electrodes in the form of solder balls.

The above semiconductor device is also characterized in that the terminals of the semiconductor chip are arranged along a substantially center line between a pair of sides of the semiconductor chip on the terminal-end surface of the semiconductor chip, and the leads are arranged in two facing sets along the sides of the semiconductor chip, respectively, in such a fashion that the terminals of the semiconductor chip are interposed between the two facing lead sets. The lead frame of the present invention is characterized in that it comprises: a plurality of leads each including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of a semiconductor chip, an outer terminal portion adapted to be

connected to an associated one of terminals of an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other; each of the outer terminal portions of the leads being protruded in a direction orthogonal to a lead frame surface via an associated one of the connecting lead portions; the inner lead portions of the leads being arranged in pair in such a fashion that the leads of each lead pair have facing tips, respectively; connecting portions each adapted to connect the facing tips of the leads included in an associated one of the lead pairs; and an outer frame portion arranged outside the outer terminal portions and connected to the connecting lead portions in such a fashion that they form an integral structure together, thereby protecting the entire portion of the lead frame. The above lead frame can be embodied into a lead frame for a BGA (Ball Grid Array) type resin encapsulated semiconductor device by arranging a plurality of leads each having an inner terminal portion and an outer terminal portion integral with each other in a two-dimensional fashion on the terminal-end surface of the semiconductor chip and forming the outer electrodes in the form of solder balls.

The present invention is also characterized by a method for fabricating a semiconductor device including a semiconductor chip, a plurality of leads fixedly attached

to a terminal-end surface of the semiconductor chip by an insulating adhesive interposed between the semiconductor chip and the leads, each of the leads including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of the semiconductor chip, an outer terminal portion extending outwardly in a direction orthogonal to the terminal-end surface of the semiconductor chip and adapted to be connected to an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other; and outer electrodes each connected to the outer terminal portion of an associated one of the leads and made of solder to allow the semiconductor device to be mounted on a circuit board, at least a part of the outer leads being externally exposed from a resin encapsulate, comprising the steps of: (A) fabricating a lead frame including a plurality of leads each including integral portions, that is, an inner terminal portion adapted to be electrically connected to an associated one of terminals of a semiconductor chip, an outer terminal portion adapted to be connected to an associated one of terminals of an external circuit, and a connecting lead portion adapted to connect the inner and outer terminal portions to each other, each of the outer terminal portions of the leads being protruded in a direction orthogonal to a

lead frame surface via an associated one of the connecting lead portions, the inner lead portions of the leads being arranged in pair in such a fashion that the leads of each lead pair have facing tips, respectively, connecting portions each adapted to connect the facing tips of the leads included in an associated one of the lead pairs, and an outer frame portion arranged outside the outer terminal portions and connected to the connecting lead portions in such a fashion that they form an integral structure together, thereby protecting the entire portion of the lead frame; (B) applying an insulating layer to a surface of the lead frame opposite to the outer terminal portions, punching out the connecting portions adapted to connect facing ones of the inner lead portions to each other along with portions of the insulating layer respectively arranged at regions corresponding to the connecting portions by use of punching dies, aligning the punched portions of the lead frame with the terminals of the semiconductor chip, and mounting the entire portion of the lead frame on the semiconductor chip by the adhesive interposed therebetween; (C) cutting off unnecessary portions of the lead frame including the outer frame portion by use of punching dies, thereby removing the cut-off portions; (D) wire-bonding the terminals of the semiconductor chip with tips of the inner terminal portions mounted on the semiconductor chip, and

encapsulating the semiconductor chip and the lead frame by
a resin while allowing a surface of the lead frame toward
the outer terminal portions to be externally exposed; and
(E) forming outer electrodes made of solder on the exposed
5 lead frame surface toward the outer terminal portions.

(FUNCTIONS)

With the above mentioned configuration, the resin
encapsulated semiconductor device of the present invention
10 can increase the occupancy degree of the chip while
achieving a miniaturization thereof. That is, the resin
encapsulated semiconductor device is capable of reducing
the mounting area thereof on a circuit board and achieving
an improvement in the mounting density thereof on the
15 circuit board. In particular, the present invention
achieves a miniaturization of the semiconductor device by
fixedly attaching a plurality of leads each including an
inner terminal portion and an outer terminal portion
integral with each other to a surface of a semiconductor
20 chip by an insulating adhesive layer interposed between the
semiconductor chip and the leads, and connecting outer
electrodes made of solder to the outer terminal portions,
respectively. Also, the present invention achieves an
increase in the number of pins in the semiconductor device
25 by arranging the outer electrodes made of solder in a two-

dimensional fashion on a plane parallel to the surface of the semiconductor chip. Where the outer electrodes made of solder are formed in the form of solder balls and arranged in a two-dimensional fashion, a BGA type semiconductor device capable of achieving an increase in the number of pins can be obtained. In the above semiconductor device, the terminals of the semiconductor chip are arranged along a substantially center line between a pair of sides of the semiconductor chip on the terminal-end surface of the semiconductor chip, and the leads are arranged in two facing sets along the sides of the semiconductor chip, respectively, in such a fashion that the terminals of the semiconductor chip are interposed between the two facing lead sets. Thus, the semiconductor device has a simple structure suitable in regard to productivity. The lead frame of the present invention makes it possible to fabricate the above mentioned resin encapsulated semiconductor device by virtue of there above mentioned configuration thereof. However, this lead frame can be fabricated using a half etching method during an etching process as used for conventional lead frames. The method for fabricating a resin encapsulated semiconductor device in accordance with the present invention involves the steps of applying an insulating layer to a surface of the lead frame opposite to the outer terminal portions, punching out

the connecting portions adapted to connect facing ones of the inner lead portions to each other along with portions of the insulating layer respectively arranged at regions corresponding to the connecting portions by use of punching dies, aligning the punched portions of the lead frame with the terminals of the semiconductor chip, and mounting the entire portion of the lead frame on the semiconductor chip by the adhesive interposed therebetween, and cutting off unnecessary portions of the lead frame including the outer frame portion by use of punching dies, thereby removing the cut-off portions. Thus, a plurality of leads each including an inner terminal portion and an outer terminal portion integral with each other are mounted on a semiconductor chip. Accordingly, the present invention makes it possible to achieve a miniaturization of semiconductor devices. In accordance with the present invention, it is also possible to fabricate a resin encapsulated semiconductor device having an increased number of pins.

[EMBODIMENTS]

Hereinafter, embodiments of the present invention associated with resin encapsulated semiconductor devices will be described in conjunction with the annexed drawings.

Fig. 1A is a cross-sectional view schematically

illustrating a resin encapsulated semiconductor device according to an embodiment of the present invention. Fig. 1B is a perspective view illustrating an essential part of the resin encapsulated semiconductor device. Figs. 1A and 5 1B, the reference numeral 100 denotes the resin encapsulated semiconductor device, 101 a semiconductor chip, 102 leads, 102A inner terminal portions, 102B outer terminal portions, 102C connecting lead portions, 101A contacts (pads), 103 wires, 104 an insulating adhesive, 105 a resin encapsulate, 106 outer electrodes made of solder (paste), respectively. The resin encapsulated semiconductor device according to this embodiment is fabricated using a lead frame which will be described hereinafter. In this resin encapsulated semiconductor device, a plurality of L-shaped leads 102, each of which 15 has an inner terminal portion 102A and an outer terminal portion 102 integral with each other, are mounted on a semiconductor chip 101 by means of an insulating adhesive 104. An outer electrode 106, which is made of solder, is 20 attached to each outer terminal portion 102B. The outer electrode 106 is outwardly protruded from a resin encapsulate 105. The resin encapsulated semiconductor device configured as mentioned above has a package area substantially equal to the entire area thereof. When this 25 semiconductor device is mounted on a circuit board, the

solder is melted and then solidified to allow the outer terminal portions 102B to be electrically connected to an external circuit. In the resin encapsulated semiconductor device according to the illustrated embodiment, contacts (pads) 101A provided at the semiconductor chip 101 are arranged in pairs along a center line L of the semiconductor chip 101 at opposite sides of the center line L in such a fashion that contacts included in each contact pair face each other. The outer terminal portion 102B of each lead is spaced apart from the inner terminal portion 102A of the lead. Between the inner and outer terminal portions 102A and 102B, a connecting lead portion 102C is interposed. The connecting lead portion 102C of each lead is bent in a direction orthogonal to the major surface of the semiconductor chip at a position near an associated one of the side surfaces of the semiconductor chip 101, so that it has an L shape. In each lead, the outer terminal portion 102B is arranged at an end of the connecting lead portion 102C. The outer terminal portions 102B of the leads are arranged in a one-dimensional fashion on a plane parallel to the major surface of the semiconductor chip 101. That is, the outer terminal portions 102B are arranged in two lines at opposite sides of the center line L. As mentioned above, one outer electrode 106 made of solder is connected to the outer terminal portion 102B of

each lead and outwardly exposed from the resin encapsulate
105.

For the insulating adhesive 104, a polyimide-based
thermoplastic adhesive having a thickness of 100 μ m (HM122C
5 manufactured by Hitachi Chemical Co., Ltd.) is preferably
used. Alternatively, a silicon denaturalized polyimide
adhesive (ITA1715 manufactured by Sumitomo Bakelite Co.,
Ltd.) or a thermosetting adhesive (HG5200 manufactured by
Tomoekawa Papermaking Co., Ltd.) may be used. Although
10 outer electrodes made of solder paste are used in the
illustrated embodiment, solder balls may be used.

As mentioned above, the resin encapsulated
semiconductor device according to the illustrated
embodiment has a package area substantially equal to the
15 entire area thereof. That is, the illustrated embodiment
of the present invention provides a package having a
compact structure in regard to area. In accordance with
the present invention, a thinned package structure can also
be provided in that it is also possible to reduce the
20 package thickness to about 1.0 mm or less. Although the
outer electrodes have been described as being arranged in
two lines along the contacts (pads) of the semiconductor
chip, they may be arranged in a two-dimensional fashion.
This is achieved by arranging contacts of the semiconductor
25 chip in a two-dimensional fashion. On the surface of the

semiconductor chip arranged with those contacts, a plurality of terminal sets each having an inner terminal and outer terminal integral with each other are arranged in a two-dimensional fashion. In this case, it is possible to
5 fabricate a semiconductor device using a semiconductor chip with an increased number of pins.

An embodiment of the present invention associated with a lead frame will now be described. The lead frame according to this embodiment is adapted to be used in the
10 above mentioned semiconductor device. Fig. 2 is a plan view of the lead frame according to this embodiment. In Fig. 2, the reference numeral 200 denotes a lead frame, 201 inner terminal portions, 202 outer terminal portions, 203 connecting lead portions, 204 a connecting portion, and 205
15 an outer frame portion, respectively. The lead frame is made of 42 ALLOY (namely, an Fe alloy containing 42% Ni). The lead frame has a thickness of 0.05 mm at its thinner portion, that is, the inner terminal portions, and a thickness of 0.2 mm at its thicker portion, that is, the
20 outer terminal portions. The connecting portion, which connects facing tips of the inner terminal portions to each other, has a thickness of 0.05 mm corresponding to that of the thinner portion. This connecting portion has a
25 structure capable of allowing an easy punching thereof in the fabrication of the semiconductor device, as described

hereinafter. Although the outer terminal portions 202 have a ball shape in the illustrated embodiment, they are not limited to this shape. Also, although the lead frame has been described as being made of the 42 ALLOY, it is not limited to this material. For the lead frame, a copper-based alloy may be used.

Now, fabrication of the lead frame according to the illustrated embodiment will be described in brief. Fig. 4 illustrates a process for fabricating the lead frame according to the illustrated embodiment. First, a lead frame blank 300 having a thickness of 0.2 mm was prepared which is made of a 42 ALLOY (an Fe alloy containing 42% Ni). The prepared lead frame blank 300 was then subjected to a cleaning process, thereby removing grease from the surfaces thereof (Fig. 3a). Subsequently, photoresist films 301 were coated over both surfaces of the lead frame blank 300, respectively. The coated photoresist films 301 were then dried (Fig. 3b).

Using desired pattern plates, the photoresist films 301 on both surfaces of the lead frame blank 300 were exposed to light at their desired portions. A developing process was then conducted to the light-exposed photoresist films 301, thereby forming photoresist patterns 301A.

For the photoresist films, a negative liquid-phase resist (PMER resist) manufactured by Tokyo Ohka Co., Ltd.

was used. Using the resist patterns 301A as anti-etch films, the lead frame blank 300 was subjected to a spray etching process at both surfaces thereof. The spray etching process was conducted using a ferric chloride solution of 48 BAUME at 57 °C. Thus, a lead frame having a structure of Fig. 2a was obtained (Fig. 3d). Fig. 2a is a plan view of the lead frame. Fig. 2b is a cross-sectional view taken along the line A1 - A2 of Fig. 2a. Thereafter, the remaining photoresist thin films were peeled off. The resulting structure was then subjected to a cleaning process. A gold plating process was subsequently conducted for desired portions of the lead frame, that is, regions including inner terminal portions (Fig. 3e).

In the fabrication process of the lead frame, the etching process was conducted with a large etch depth at one major surface of the lead frame blank where outer terminal portions are to be formed, and with a small etch depth at the other major surface of the lead frame. In place of the gold plating, silver or palladium plating may be utilized. The above mentioned lead frame fabrication process is adapted to manufacture a single lead frame required for the manufacture of a single semiconductor device. In terms of productivity, however, the etching process is conducted for lead frame units each corresponding to the single lead frame shown in Fig. 2. To

this end, a frame member (not shown) is provided at a desired portion of the peripheral edge of the lead frame so as to connect a desired part of the outer frame portion 205 shown in Fig. 2 to a corresponding one of an adjacent lead frame.

Using the lead frame fabricated as mentioned above, the resin encapsulated semiconductor device according to the present invention was fabricated. Now, a method for fabricating the resin encapsulated semiconductor device in accordance with an embodiment of the present invention will be described. Fig. 4 illustrates the method for fabricating the resin encapsulated semiconductor device in accordance with the embodiment of the present invention. A polyimide-based thermosetting insulating adhesive (tape) 401 (HM122C manufactured by Hitachi Chemical Co., Ltd.) was applied to one surface, formed with the outer terminal portions 402, of the lead frame 400 fabricated as in Fig. 3 and the outer surface of the lead frame 400 using a hot pressing process conducted at 400 °C and 6 Kg/m² for 1.0 second (Fig. 4a). The resulting structure is shown in Fig. 5 which is a plan view. Thereafter, the connecting portions 403 connecting facing tips of the inner terminal portions were punched using punching dies 405A and 405B (Fig. 4b). Also, portions of the insulating adhesive

(tape) corresponding to those connecting portions 403 were punched (Fig. 4c).

Subsequently, unnecessary portions of the lead frame including the outer frame 404 were cut off using outer frame punching and pressing dies 406A and 406B (Fig. 4d).
5 The lead frame was then bonded to a semiconductor chip 407 at its leads 410 under pressure while applying heat (Fig. 4e).

The process for cutting off the unnecessary portion of the lead frame including the outer frame 404 supporting
10 the entire portion of the lead frame along with the connecting lead portion, as shown in Fig. 4d, may be carried out after an resin encapsulating process. In this case, dam bars (not shown) are preferably provided, as in
15 QFP packages typically using a lead frame having a single layer structure. After the mounting of the leads 410 on the semiconductor chip 411, the inner terminal portion 410 of each lead 410 was electrically connected to an associated one of terminals (pads) 411A of the
20 semiconductor chip 411 (Fig. 4f).

Subsequently, an epoxy-based resin 415 was molded to encapsulate the resulting structure while exposing the outer terminal portions 410B of the leads 410 using a desired mold (Fig. 4g).

Although a specific mold (not shown) was used for the above process in the illustrated case, use of such a die may be unnecessary in so far as the resin encapsulating process can be conducted under the condition in which
5 desired portions (outer terminal portions) of the lead frame are left. Thereafter, a solder paste was coated on the exposed outer terminal portions 410B in accordance with a screen printing process, thereby forming outer electrodes
416 made of solder (paste). Thus, the fabrication of the
10 resin encapsulated semiconductor device according to the present invention was achieved (Fig. 4h).

Although the formation of the outer electrodes 416 made of solder has been described as being achieved using a screen printing process, it may be achieved using a reflow
15 or bonding process in so far as an amount of solder required for a connection of the semiconductor device to a circuit board is obtained.

(EFFECTS OF THE INVENTION)

20 As apparent from the above description, the present invention makes it possible to increase the occupancy degree of a semiconductor chip in a semiconductor package in situations requiring new resin encapsulated
semiconductor devices having a highly integrated structure
25 while exhibiting a high performance. The present invention

also makes it possible to reduce the area of the semiconductor device on a circuit board in order to cope with a compactness of the semiconductor device. That is, the present invention can provide a semiconductor device capable of achieving an improvement in the mounting density on a circuit board. At the same time, the present invention can provide a resin encapsulated semiconductor device having a new multipinned structure which could not be realized in compact packages such as conventional TSOPs.